**THE UNITED STATES OF AMERICA****TO ALL TO WHOM THESE PRESENTS SHALL COME:**

**UNITED STATES DEPARTMENT OF COMMERCE**  
**United States Patent and Trademark Office**

*October 14, 2004*

**THIS IS TO CERTIFY THAT ANNEXED HERETO IS A TRUE COPY FROM THE RECORDS OF THE UNITED STATES PATENT AND TRADEMARK OFFICE OF THOSE PAPERS OF THE BELOW IDENTIFIED PATENT APPLICATION THAT MET THE REQUIREMENTS TO BE GRANTED A FILING DATE.**

**APPLICATION NUMBER: 60/505,384**  
**FILING DATE: September 23, 2003**  
**RELATED PCT APPLICATION NUMBER: PCT/US04/31274**

Certified by

**Jon W Dudas**

**Acting Under Secretary of Commerce  
for Intellectual Property  
and Acting Director of the U.S.  
Patent and Trademark Office**



**BEST AVAILABLE COPY**

18351 U.S. PTO  
09/23/03

**PROVISIONAL APPLICATION FOR PATENT COVER SHEET**

This is a request for filing a PROVISIONAL APPLICATION FOR PATENT under 37 CFR 1.53(c).

Express Mail Label No. ER 536529235 US

**INVENTOR(S)**

Given Name (first and middle [if any])	Family Name or Surname	Residence (City and either State or Foreign Country)
Jason Joseph M. Stephen R. Jason Derek Jennifer	Rolland DeSimone Quake Yarbrough Schorzman Kelly	Chapel Hill, NC Chapel Hill, NC San Marino, CA Chapel Hill, NC Chapel Hill, NC Chapel Hill, NC

22151 U.S. PTO  
60/505384

09/23/03

☐ Additional inventors are being named on the \_\_\_\_\_ separately numbered sheets attached hereto

**TITLE OF THE INVENTION ( 280 characters max )**

Photocurable Pefluoropolyethers for use as Novel Materials in Microfluidic Devices

Direct all correspondence to :

**CORRESPONDENCE ADDRESS**

☒ Customer Number

000029690

OR

Place Customer Number  
Bar Code Label here  
PATENT TRADEMARK OFFICE

**ENCLOSED APPLICATION PARTS (check all that apply)**

☒ Specification Number of Pages 3

☐ CD(s), Number \_\_\_\_\_

☐ Drawing(s) Number of Sheets \_\_\_\_\_

☐ Application Data Sheet. See 37 CFR 1.76

☒ Other (specify)

Postcard

**METHOD OF PAYMENT OF FILING FEES FOR THIS PROVISIONAL APPLICATION FOR PATENT**

☒ Applicant claims small entity status. See 37 CFR 1.27.

☐ A check or money order is enclosed to cover the filing fees.

☒ The Commissioner is hereby authorized to charge filing fees or credit any overpayment to Deposit Account Number:

50-1742

☐ Payment by credit card. Form PTO-2038 is attached.

FILING FEE  
AMOUNT (\$)

80

The invention was made by an agency of the United States Government or under a contract with an agency of the United States Government.

☒ No

☐ Yes, the name of the U.S. Government agency and the contract number are:

Respectfully submitted,

SIGNATURE

*Rich W. If*

Date

9/23/2003

REGISTRATION NO.

47,319

TYPED or PRINTED NAME: Rich W If

(if appropriate)  
Docket Number:

CIT-3951-P

TELEPHONE: (626) 395-2322

the PTO did not receive the following listed items (s):

BEST AVAILABLE COPY

## DESCRIPTION OF INVENTION:

Describe the invention in detail. Attach additional pages as necessary.


The invention described involves the use of photocurable perfluoropolyether materials to formulate microfluidic devices by soft lithography. Soft lithography is the process by which a liquid prepolymer is poured over a patterned silicon wafer. The liquid prepolymer is then crosslinked and when delaminated from the wafer creates a "stamp" of the desired pattern. PDMS materials are the current prepolymers of choice for such processes.

The increasing complexity of microfluidic devices has created a demand to use them in a rapidly growing number of applications. However, the swelling of the PDMS device by organic solvents drastically disrupts its micron-size features. Thus, these applications are limited to the use of fluids such as water that do not swell PDMS. A material that could be formulated into a microfluidic device that did not swell in typical organic solvents such as methylene chloride yet retained the mechanical properties of PDMS is greatly desired and could open the door to a wide variety of applications which are inaccessible by current PDMS materials.


Perfluoropolyethers (PFPEs) are a class of fluoropolymers that are widely known for their hydrophobic and lyophobic properties. For this reason they are often employed as lubricants on high-performance machinery operating in harsh conditions. Since they have similar viscosities compared to Sylgard 184 prepolymers, they are ideal candidates for a novel class of solvent-resistant microfluidic devices.

Bongiovanni et. al. have previously reported the synthesis of functionalized UV-curable perfluoropolyethers (*Macromol. Chem. Phys.* 198, 1893-1907(1997)). Using a slightly modified procedure, we have synthesized and cured the same materials. The novelty of this invention lies in the use of these materials in the fabrication of microfluidic devices. Shown below is an outline of our synthetic methodology.

Scheme 1. Synthesis of functionalized PFPE prepolymers



Once this functionalized material is isolated and purified, we are able to crosslink it photochemically through the addition of a free radical photoinitiator to form a miscible blend and subsequent exposure to UV light for five minutes. This procedure is outlined below.




### Crosslinked PFPE Network

**Scheme 2. Photocuring of functionalized PFPE prepolymers**

As was previously mentioned, the novelty of this invention is in the formation of microfluidic devices with this material using the described curing process. Shown in Figure 1 is a cartoon illustration of how that process will occur.

**Figure 1. Illustration of proposed device fabrication using UV-curable PFPE materials**



- a. Write a brief descriptive abstract of the invention without disclosing any confidential information. This may be used for marketing purposes.

The invention described involves the usage of novel functionalized PFPE materials in the fabrication of microfluidic devices by "soft lithography." These advanced materials will allow for the fabrication of devices that will enable microfluidics technology to expand into applications that are currently unreachable due to swelling of the current PDMS-based devices by organic solvents.

- b. Expand on novel and unusual features which distinguish this invention from present technology. What problems does the invention solve or what advantages does it possess?

Our experiments have shown fully cured Sylgard 184 to swell up to 94 wt% in methylene chloride. Such swelling will seriously disrupt the micron-sized channels in microfluidic devices and render them useless. In contrast, our PFPE materials showed only 2 wt% swelling after soaking in methylene chloride for 5 days. The invention solves this swelling problem and allows for microfluidics technology to expand into novel applications that utilize organic solvents.

- c. Comment on possible uses for the invention. In addition to immediate applications, are there other uses that might be realized in the future?

Microfluidics technology has far-reaching applications. In a recent article in *The Industrial Physicist* (August/September 2003, pg 14), Kevin Killeen of Agilent is quoted as saying " Microfluidics is going to revolutionize the way things are done... It's going to miniaturize chemistry and make possible chemical reactions that can't be done in batch mode today....it will touch virtually every aspect of our lives." The technology has found applications in ink-jet printers, lab-on-a-chip assays, pharmaceuticals, biotechnology, chemical sensors for defense, and agriculture. However, all of these applications are limited in that only fluids that do not swell Sylgard 184 can be used. The present invention opens the door to a wider span of applications through the lyophobic nature of the PFPE networks.

- d. Describe any disadvantages or limitations of the invention. Can they be overcome? How?

The only disadvantage of the use of PFPE materials is the cost. PFPEs are much more expensive than PDMS materials. However, microfluidics technology utilizes only minute quantities of the prepolymer, thus the cost of these materials is virtually a non-issue.

- e. Are there known inventions or products that would compete with this one? Please describe, including information on relevant patents and publications, if available.

As described previously, the PDMS prepolymers, commercially known as Sylgard 184 are the current materials of choice for microfluidics.

- g. Are there any prior patent applications or patents by the inventor(s) related to this invention? If so, list the serial number(s) and filing date(s).

There are no such patents or patent applications

# Document made available under the Patent Cooperation Treaty (PCT)

International application number: PCT/US04/031274

International filing date: 23 September 2004 (23.09.2004)

Document type: Certified copy of priority document

Document details: Country/Office: US  
Number: 60/505,384  
Filing date: 23 September 2003 (23.09.2003)

Date of receipt at the International Bureau: 22 October 2004 (22.10.2004)

Remark: Priority document submitted or transmitted to the International Bureau in compliance with Rule 17.1(a) or (b)



World Intellectual Property Organization (WIPO) - Geneva, Switzerland  
Organisation Mondiale de la Propriété Intellectuelle (OMPI) - Genève, Suisse